

FIXODROP ES/BS 8980-8981-8982


Wash-resistant epilame



Description

Epilamination is a surface treatment intended to lower the surface tension of the support thus preventing the spreading of liquid lubricants. It provides the highest possible degree of security for mechanical precision instruments.

Fixodrop ES/BS is a modern epilame, developed by MOEBIUS, based on fluorinated synthetic resins, diluted in a solvent which meets current ecological standards.



Technical features (indicative values)

Nano metric film	Invisible
Active material	Fluorinated polyester
Diluent	Ecosolv (Art. 5700)
Density at 20 °C	1,59 g/ml
Boiling point	110 °C
Flash point	non-flammable
Toxicity	non toxic
Ozone depletion potential	0 (ODP)
Atmospheric life time	< 10 days
Thickness epilame film	approx. 3 - 5 nm
Superficial tension	approx. 20 mN/m
Stability epilame film	until 150 °C
Compatibility	All types of materials

Application fields

Fixodrop is successfully used in the following application areas :

- Hydrophobic and oleophobic (epilame) surface treatment for mechanisms, electronic and mechanical parts:
- Precision micromechanics (watch, timer, measuring devices, tools, ...)
- Instrumentation and counters (automotive, aeronautic, naval,...)
- Cameras and optical instruments
- General mechanics (office equipment, fans,...)

Our range

Fixodrop ES/BS 8980	▶ Concentrate
Fixodrop ES/BS-10 8981	▶ Ready-to-use solution
Fixodrop ES/BS-20 8982*	▶ Ready-to-use solution

Important : Fixodrop concentrate 8980 may only be dissolved with our EcoSolv solvent.

*This ready-to-use solution is recommended only at a production level with excellent working conditions and regular checks.

Implementation

Preparation of the support before use:

- All parts in contact with lubricants should always be treated.
- Before Fixodrop treatment, all parts must be cleaned and dried. This step is important and strongly influences the behavior of the epilame.
- Fixodrop-treated anchor pallets should be lubricated only after running dry for 1 to 2 minutes.

Dipping application for the epilame film :

- The parts are immersed and slightly shaken for a minimum of 30 seconds in the Fixodrop ES/BS bath. The epilame can also be applied by spraying.

Drying :

- After immersion the pieces are drained by stirring and immediately dried, preferably by a stream of hot air at about 60 °C.
- This treatment is necessary to guarantee a good homogeneity of the film and the esthetics of the piece.

Advices :

- In order to avoid uncontrolled loss of the diluent by evaporation, the Fixodrop bath should immediately be sealed after each use.
- For large baths a cooling system and solvent recycling is advantageous!
- The cleanliness of the bath is to be checked regularly. In case of appearance of dust or other impurities, the bath should be filtered or changed.

Storage

We advise keeping Moebius products in their original packaging in a clean and dry place, protected from light, ideally at a temperature of 15 to 26 °C.

After opening we recommend keeping the products for a maximum of 12 months.



FIXODROP ES/BS 8980-8981-8982


Wash-resistant epilame



Contact angles

Measurements of contact angles after epilamization and after 3 consecutive washing cycles with a Rubisol type detergent. Without the presence of epilame, Test Oil #3 spreads very strongly. It is a generally used reference to test epilames.

9703 (Test oil #3)



The synthetic universal oil 9010 is used for high precision mechanics. It is representative of horological oils.

Synt-A-Lube 9010

